



Centre Court,
Meridian Business Park, Leicester
LE19 1WD, United Kingdom

Tel: +44 (0) 116 263 0330
Fax: +44 (0) 116 263 0311/12
Web: www.intertek.com/consumergoods

TEST REPORT

NUMBER: LECH00326454

APPLICANT: Allied International Trading Ltd
t/a Supertouch
Unit A1, Hubert Road
Brentwood
Essex
CM14 4JE

DATE: 20th December 2011

For the attention of Paul Ansell

SAMPLE DESCRIPTION: Blue Vynatrilite Gloves

REFERENCE / STYLE NO.: 11511-4 S - XL

RETAILER: Supertouch B.S.

SAMPLE RECEIVED: 8th December 2011

PURCHASE ORDER: Paul Ansell

TEST REQUEST: Plastic Materials and Articles in Contact with Foodstuffs, European Directive 2002/72/EC and amendments (overall migration) (Single Use)

CONCLUSION: See comments on page 2.

Tests marked (*) in this Test Report are not included in the UKAS Accreditation Schedule for this Laboratory
Tests marked (^) in this Test Report have been sub-contracted to an agent approved by Intertek
Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation



TEST REPORT

NUMBER: LECH00326454

Specification: Plastic Materials and Articles in Contact with Foodstuffs, European Directive 2002/72/EC

Sample: Blue Vynatrile Glove

Conclusion: The overall migration limit of 10mg/dm² is specified by the EC Directive 2002/72/EC. The above samples therefore **comply** with the overall migration limit for single exposure to Simulant B and Milk.

The overall migration limit for 10mg/dm² is specified by the EC Directive 2002/72/EC. The above samples therefore **do not comply** with the overall migration limit for single exposure to Simulant D (95% ethanol).

Simulants: B – 3% Acetic Acid
D – 95 % ethanol
Milk – 50% ethanol in water

Temperature: B, Milk - 40°C
D - 40°C

Exposure Time: 0.5hours
Exposure Cycle: Single Use

Testing was carried out by Immersion.

Results

Sample no.	Description	Average Migration (mg/dm ²)	Limit (mg/dm ²)
1	Simulant B	<1.0	10.0
2	Milk Simulant	<1.0	10.0
3	Simulant D	73.8	10.0

Measured surface area: 3.7dm²
Volume (L): 0.11
Surface area to Volume ratio: 33.6

Date of Testing: 16th-20th December 2011



Centre Court,
Meridian Business Park, Leicester
LE19 1WD, United Kingdom

Tel: +44 (0) 116 263 0330
Fax: +44 (0) 116 263 0311/12
Web: www.intertek.com/consumergoods

TEST REPORT

NUMBER: LECH00326454



END OF REPORT

PAGE 3 OF 3