



Centre Court,
Meridian Business Park, Leicester
LE19 1WD, United Kingdom

Tel: +44 (0) 116 263 0330
Fax: +44 (0) 116 263 0311/12
Web: www.intertek.com/consumergoods

TEST REPORT

NUMBER: LECH00327217

APPLICANT: Allied International Trading Ltd
t/a Supertouch
Unit A1, Hubert Road
Brentwood
Essex
CM14 4JE

DATE: 27th January 2012

For the attention of Paul Ansell

SAMPLE DESCRIPTION: Blue 60 Micron LD Polyethylene Material

REFERENCE / STYLE NO.: PE Apron 60 Micron Blue (41612, 41613, 41712, 41713)

RETAILER: Supertouch L021

SAMPLE RECEIVED: 12th January 2012

PURCHASE ORDER: Paul Ansell

TEST REQUEST: Plastic Materials and Articles in Contact with Foodstuffs, European Directive 2002/72/EC and amendments (overall migration) (Single Use)

CONCLUSION: See comments on page 2.

Tests marked (*) in this Test Report are not included in the UKAS Accreditation Schedule for this Laboratory
Tests marked (^) in this Test Report have been sub-contracted to an agent approved by Intertek
Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation



Centre Court,
Meridian Business Park, Leicester
LE19 1WD, United Kingdom

Tel: +44 (0) 116 263 0330
Fax: +44 (0) 116 263 0311/12
Web: www.intertek.com/consumergoods

TEST REPORT

NUMBER: LECH00327217

Specification: Plastic Materials and Articles in Contact with Foodstuffs, European Directive 2002/72/EC

Sample: Blue 60 Micron LD Polyethylene Material

Conclusion: The overall migration limit of 10mg/dm² is specified by the EC Directive 2002/72/EC. The above samples therefore **comply** with the overall migration limit for single exposure to simulant B, C and Milk.

Simulants: B – 3% Acetic Acid
C – 10% ethanol in water
Milk – 50% ethanol in water

Temperature: B, C, Milk - 40°C

Exposure Time: 0.5 hours
Exposure Cycle: Single Use

Testing was carried out by Immersion.

Results

Sample no.	Description	Average Migration (mg/dm ²)	Limit (mg/dm ²)
1	Simulant B	2.2	10.0
2	Simulant C	<1.0	10.0
3	Milk Simulant	<1.0	10.0

Measured surface area: 1.0
Volume (L): 0.1
Surface area to Volume ratio: 10

Date of Testing: 24th-26th January 2012



Centre Court,
Meridian Business Park, Leicester
LE19 1WD, United Kingdom

Tel: +44 (0) 116 263 0330
Fax: +44 (0) 116 263 0311/12
Web: www.intertek.com/consumergoods

TEST REPORT

NUMBER: LECH00327217



END OF REPORT